



Established in 2003
NINGBO BODI Seals Co.,Ltd
Global technical advisor and a leading manufacturer of sealing solutions
Website: www.bdseals.com

FFKM-BD375B Materials data sheets

FFKM-BD375B has excellent resistance to chemicals, organic and inorganic acids, alkalis, esters, ethers, ketones, aldehydes, hot water and water vapor, etc., with low metal ion precipitation. The maximum use temperature is 250°C

- **Characterization:**
 - Extensive chemical resistance
- **Temp range:**
 - -10°C - 250°C
- **Application:**
 - Chemical industry

ORIGINAL PROPERTIES

ORIGINAL PROPERTIES	ASTM	Typical Test
Hardness Shore A	D2240	75
Color	Black	Black
Tensile strength Mpa	D412	21.2
Elongation at break %	D412	183
Compression Set 25% 70Hrs @200°C	D395B	17.1
Specific gravity		2.0