



Established in 2003
NINGBO BODI Seals Co.,Ltd
Global technical advisor and a leading manufacturer of sealing solutions
Website: www.bdseals.com

FFKM-BD375W Materials data sheets

FFKM-BD375W Perfluoroelastomer parts are a white product with excellent resistance to chemical properties. It has good resistance to oxygen, fluorine based plasma. It also has excellent thermal stability, compression permanent deformation properties. It is suitable for etching, deposition and other corrosive Higher working conditions, the maximum use temperature is 250°C

- **Characterization:**

- Cleanings

- **Temp range:**

- -10°C - 250°C

- **Application:**

- Semiconductor industry

ORIGINAL PROPERTIES

Hardness Shore A

Color

Tensile strength Mpa

Elongation at break %

Compression Set 25% 70Hrs @200°C

Specific gravity

ASTM

D2240

White

D412

D412

D395B

Typical Test

75

White

20.2

195

10.6

2.1