



Established in 2003
NINGBO BODI Seals Co.,Ltd
Global technical advisor and a leading manufacturer of sealing solutions
Website: www.bdseals.com

FFKM-BD675B Materials data sheets

FFKM-BD has excellent chemical corrosion resistance and can resist organic acid, inorganic acid, alkali, ester, ether, ketone, aldehyde, superheated water and water vapor, etc., with low metal ion precipitation. The maximum use temperature is 230°C.

- **Characterization:**

- Pyridine

- **Temp range:**

- -10°C - 230°C

- **Application:**

- Chemical industry

ORIGINAL PROPERTIES

Hardness Shore A

Color

Tensile strength Mpa

Elongation at break %

Compression Set 25% 70Hrs @200°C

Specific gravity

ASTM

D2240

Black

D412

D412

D395B

Typical Test

75

Black

20.5

190

19.2

2.0